

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2001-068760

(43)Date of publication of application : 16.03.2001

(51)Int.Cl.

H01L 43/08

G11B 5/39

H01F 10/30

(21)Application number : 11-244755

(71)Applicant : HITACHI LTD

(22)Date of filing : 31.08.1999


(72)Inventor : ARAI REIKO
KAWATO YOSHIAKI
WATANABE KATSURO

(54) FERROMAGNETIC TUNNEL JUNCTION ELEMENT

(57)Abstract:

PROBLEM TO BE SOLVED: To suppress the reduction in the magnetoresistance effect due to destruction of a tunnel barrier layer and thereby achieve uniformity and reproducibility, by arranging an amorphous ferromagnetic layer on at least the interface of one of a ferromagnetic layer and the tunnel barrier layer.

SOLUTION: A base film 22 for improving the orientability of a free layer 11 of a ferromagnetic tunnel junction, the layer 11, and an amorphous ferromagnetic layer 15 for improving heat resistance are formed on an oxide layer- deposited silicon substrate 21. A tunnel barrier layer 12 is formed on the layer 15 by preparing an Al layer, and oxidizing the surface of the Al layer by a plasma oxidation method. Further, a fixed layer 13, an antiferromagnetic layer 14, and a protection film 23 are sequentially formed. Next, a lower electrode layer 26 and an upper electrode layer 27 are processed into predetermined configurations. Further, an Al₂O₃ insulating layer 24 for preventing contact between the layers 26 and 27 is formed, and then patterned, and for contact with the lower/upper electrode layers 27 and 28, Au layers are formed as lower/ upper electrode wiring layers 25 and 26, whereby a ferromagnetic tunnel junction element 20 is prepared.



LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]